

PROTECTIEKARTON

Technische fiche

| | |
|---------------------|--|
| Total weight | 280 g/m ² |
| Board | 250 g/m ² |
| Coating | LDPE 14 gr/m ² at both sides (2 x 14gr/m ²) |
| Bursting strength | 1111 kPa |
| Thickness | 338 Micron |
| Tensile strength MD | 28 kN/m |
| Tensile strength CD | 12.7 kN/m |
| Density | 736 kg/m ³ |
| Tearing strength MD | 3729 mN |
| Tearing strength CD | 4443 mN |
| Tolerance | +/- 5% |